


optoSiC® SCANcoat 1075-H

LOW-STRESS OPTICAL COATING OPTIMIZED FOR HIGH REFLECTIVITY AT **1075NM** FOR AOI OF **45°** AND **37,5°**, RESPECTIVELY.



SCANcoat 1075-H

- u-pol 45°
- u-pol 35°
- u-pol 55°
- u-pol 37,5°
- u-pol 27,5°
- u-pol 47,5°

1075-H

		TYPICAL VALUES	
Wavelength [λ_1]	(nm)	1050 ... 1100	s. spectrum
Wavelength [λ_2]	(nm)	632,8	
Scan Angle	(°)	37,5 / 45 ± 10	27 - 55
HR [λ_1] @45° u-pol	(%)	> 99,5	
R_{avg} [λ_2] @45 u-pol	(%)	> 90	
Powerdensity	[kW/cm²]	n.d.	LIDT* [@1064nm CW]
Damage Threshold / Energy Density	[J/cm²]	n.d.	for pulsed 1064nm radiation 10ns, 1 Hz

- Laser induced damage threshold (LIDT) is typically given as x-Watts per linear millimeter of beam radius (br) (1/e²) 310% at 45° Angle of Incidence.
- Transmission edges can vary ~ 2% from lot to lot for the given wavelength.
- All data given for ambient conditions 20-25°C, at higher temperatures thermal shifts will occur.
- Reflectivity is qualified on fused silica samples
- Measured uncertainty of HR +/- 1,0 %
- n.d. = not defined



**MERSEN Deutschland
Holding GmbH & Co. KG**
Division optoSiC

Baierbrunner Straße 39
D-81379 Munich
Germany

phone +49 (0) 89 780 7239 0
fax +49 (0) 89 780 7239 211
email info.munich@mersen.com

www.optosic.com
www.mersen.com